

## **Test report**

### **ZEOCEM 200**

<b>Oil absorption number</b>	
Standard:	ISO 787-5
Sample	Micro-miller natural zeolit ZEOCEM 200
Used oil	Dibutyl phtalate (DBP)
Test date	3. 3. 2014
Number of the tests	3
<b>Test results</b>	
Test No. 1	53 ml/100 g
Test No. 2	53 ml/100 g
Test No. 3	54 ml/100 g
<b>Oil absorption number</b>	<b>53 ml/100 g</b>