

## Test report

<b>Oil absorption number</b>	
Standard:	ISO 787-5
Sample	Micro-miller natural zeolit ZEOCEM 20
Used oil	Dibutyl phtalate (DBP)
Test date	25. 4. 2013
Number of the tests	3
<b>Test results</b>	
Test No. 1	62 ml/100 g
Test No. 2	62 ml/100 g
Test No. 3	63 ml/100 g
<b>Oil absorption number</b>	<b>62 ml/100 g</b>